







<b>Botswana - jacket</b>						
<b>Description</b>	<ul style="list-style-type: none"> <li>jacket with buttons;</li> <li>2 wide front pockets;</li> <li>1 breast pocket.</li> </ul>					
						
<b>Maintenance</b>	Maximum temperature: 60°C; Do not bleach; Do not dry clean; Tumble drying possible; Drying at lower temperature; Ironing at low temperature (max 110°C).					
	    					
	<table border="1"> <tr> <td><b>item</b></td> <td>V350-0-01 navy</td> </tr> <tr> <td><b>standards</b></td> <td>EN ISO 13688:2013</td> </tr> <tr> <td><b>sizes</b></td> <td>44 – 64</td> </tr> </table>	<b>item</b>	V350-0-01 navy	<b>standards</b>	EN ISO 13688:2013	<b>sizes</b>
<b>item</b>	V350-0-01 navy					
<b>standards</b>	EN ISO 13688:2013					
<b>sizes</b>	44 – 64					

**SAFETY TECHNICAL SPECIFICATIONS**

<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>	
<b>Background fabric</b>	EN ISO 1833-1977, SECTION 10	Composition: Weave: Twill	100% cotton Warp: 68x44 [yarn/inc] Weft: 10x10 [yarn/inc]	
	EN ISO 12127:1996	Weight per unit area	270 gr/sqm	
	ISO 105X12	Colour fastness to rubbing	Dry: 4 - 5 Wet: 3 - 4	1 - 5 1 - 5
	ISO 105-C06, C2S	Colour fastness to washes (60°C)	Colour change: 4-5 Staining: 4 - 5	1 - 5 1 - 5
	ISO-105-E04	Colour fastness to perspiration	Colour change: 4-5 Staining: 4-5	1 - 5 1 - 5
	ISO-105-X11	Colour fastness to hot pressing	Dry: 4-5 Wet: 4-5	1 - 5 1 - 5
	ISO 3071:2005	The pH's determination from the watery extract	pH : 7.4	3,5<PH≤9,5
	EN ISO 13688:2013 par. 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	ISO 6330 Test N0.2A	Dimensional change to washes	Warp: - 2.9 % Weft: - 2.9 %	+/- 3%
	EN ISO 13934-2	Tensile strength	Warp: 486.3 N Weft: 267.6 N	400 N 400 N
	ISO 13937-1	Tearing strength	Warp: 22.15 N Weft: 14.24 N	25 N 25 N
	ISO 105 B02	Colour Fastness To Light	Colour change: > 5	