



COMOROS – shorts

<p>Description</p>	<ul style="list-style-type: none"> • 2 wide front pockets, • reinforced crotch, • double back pocket with flap, • elasticated waist, • ergonomic design, • side pocket, • coin pocket, • rule pocket, • front pocket on the right leg, • YKK® zip. 		
<p>Maintenance</p>	<p>Maximum wash temperature: 40 °C; Do not bleach; Dry clean with solvents on point F plus Tetrachloroethylene; Tumble drying possible - Drying at lower temperature; Ironing at low temperature (max 110 °C).</p> 	<p>Item</p>	<p>V475-0-00 khaki V475-0-01 avion V475-0-02 navy V475-0-03 clay brown V475-0-04 anthracite V475-0-05 black</p>
<p>Standards:</p>		<p>EN ISO 13688:2013</p>	
<p>Sizes</p>		<p>44 – 64</p>	

SAFETY TECHNICAL SPECIFICATIONS

	Test method	Description	Cofra result	Minimum requirement / range
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	100% cotton	
	EN ISO 12127:1996	Fabric mass per unit area	200 ±5% g/m ²	
	EN ISO 13688 :2013 4.2 (EN 14362-1:2003)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	EN ISO 13688 :2013 4.2 (EN ISO 3071:2006)	the pH's determination from the watery extract	pH=6.6	3,5 ≤pH≤ 9,5
	EN ISO 13688 :2013 5.3 (ISO 5077)	Dimensional change to washing 30°C	warp: -1.0% weft: -0.2%	±3%

ISO 105-C06	Colour fastness to Laundering at 40°C			1 - 5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
	wool	4-5		
ISO 105 D01	Colour fastness to dry cleaning			1 - 5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
	wool	4-5		
ISO 105 E04	Colour fastness to perspiration	Acidic	Alkaline	1 - 5
	<i>Colour change</i>	4-5	4-5	
	<i>Staining:</i>			
	diacetate	4-5	4-5	
	cotton	4-5	4-5	
	nylon	4-5	4-5	
	polyester	4-5	4-5	
	acrylic	4-5	4-5	
	wool	4-5	4-5	
ISO 105-X12	Colour fastness to rubbing			1-5
	<i>Staining:</i>	Dry: 4		
		Wet: 2 - 3		
EN ISO 105-X11	Colour fastness to hot pressing (110°C)			1-5
	<i>Colour change</i>			
	Dry:	4-5		
	Wet:	4-5		
ISO 105-B02	Colour fastness to light			1-5
	<i>Colour change</i>	4		
EN ISO 13934-1	Tensile strength	warp: 990 N		
		weft: 670 N		
EN ISO 13937-2	Tearing strenght	Warp: 14 N		
		Weft: 21 N		
EN ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale method	44500 cycles		