



Cotonos Aguirrezábal, S. A.

- FABRICACION DE ALGODONES Y TPAPOS PARA LIMPIEZA INDUSTRIAL
- CELULOSA INDUSTRIAL, SECAMANOS E HIGIENICOS
- BOBINAS DE TEJIDO
- ABSORBENTES INDUSTRIALES
- JABONES, DESENGRASANTES



TECHNICAL DATA SHEET

SEPIOLITE 15-30

Composition (XRD)

Sepiolite	65% (Min. 55%)
-----------	----------------

Physical properties

Density	0.65 g/cc (Max. 0.73 g/cc)
Westinghouse water absorption	130% (Min. 100%)
Westinghouse oil absorption	60% (Min. 50%)

Particle size distribution

> 1.40 mm	Max. 12%
1.40 mm - 0.25 mm	Min. 86%
< 0.25 mm	Max. 2%

Undesirable substances (2002/32/EC)

Cadmium	< 2 ppm
Lead	< 30 ppm
Dioxins	< 0.5 ng/kg
DL-PCBs	< 0.5 ng/kg