

**GALPONES – softshell jacket**

<p><b>Description</b></p>	<ul style="list-style-type: none"> <li>• 2 wide lower pockets with zip,</li> <li>• front opening with zip,</li> <li>• reflex inserts,</li> <li>• flap protecting the chin,</li> <li>• arm ergonomic design,</li> <li>• stretch fabric.</li> </ul>		
<p><b>Maintenance</b></p>	<p>Maximum wash temperature: 40 °C; Dry clean with solvents on point F plus Tetrachloroethylene; Do not bleach; Do not dry in a tumble dryer; Dry in a vertical (hanging) position after squeezing and/or spinning; Do not iron.</p>  	<p><b>Item</b></p> <p>V378-0-02 navy/black/royal, V378-0-04 anthracite/black/orange, V378-0-05 black/rust, V378-0-06 black/anthracite/lime</p>	
		<p><b>Standards:</b></p>	<p>EN ISO 13688:2013</p>
		<p><b>Sizes</b></p>	<p>S-4XL</p>

**SAFETY TECHNICAL SPECIFICATIONS**

	Test method	Description	Cofra result	Minimum requirement / range
<p><b>Background fabric</b></p>	<p>EN ISO 1833-1977, SECTION 10</p>	<p>Composition:</p>	<p>EXTERNAL: 100% polyester with COFRA-TEX membrane (TPU membrane Thermoplastic Polyurethane) INTERNAL FLEECE: 100% polyester</p>	
	<p>EN ISO 12127:1996</p>	<p>Fabric mass per unit area</p>	<p>200 ±5% g/m<sup>2</sup></p>	
	<p>EN ISO 13688:2013 5.3 (ISO 5077)</p>	<p>Dimensional change</p>	<p>warp: -1.6% weft: -2.2%</p>	<p>±3%</p>
	<p>EN ISO 13688:2013 4.2 (ISO 3071)</p>	<p>The pH's determination from the watery extract</p>	<p>pH=6,4</p>	<p>3,5 ≤ pH ≤ 9,5</p>
	<p>EN ISO 13688:2013 4.2 (EN 14362-1)</p>	<p>Search of the aromatic and carcinogenic amines</p>	<p>Not recording</p>	<p>≤30 ppm</p>

ISO 105-C06	Colour fastness to Laundering at 40°C			1 - 5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4		
	cotton	4-5		
	nylon	4		
	polyester	4		
	acrylic	4-5		
wool	4-5			
ISO 105 D01	Colour fastness to dry cleaning			1 - 5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
wool	4-5			
EN ISO 105 E04	Colour fastness to perspiration			1 - 5
	<i>Colour change</i>	4-5	4-5	
	<i>Staining:</i>			
	diacetate	4-5	4-5	
	cotton	4-5	4-5	
	nylon	4-5	4	
	polyester	4-5	4-5	
	acrylic	4-5	4-5	
wool	4-5	4-5		
ISO 105-X12	Colour fastness to rubbing			1-5
	<i>Staining:</i>	Dry: 4 - 5 Wet: 4 - 5		
ISO 105-B02	Colour fastness to light			1-5
	<i>Colour change</i>	4-5		
ISO 13938-2	Burst strength	945 KN/m <sup>2</sup>		
EN 20811	Water penetration resistance - Wp [Pa] (before each pretreatment)	Wp > 13000 Pa	CLASS 1 CLASS 2 CLASS 3	Wp ≥ 8000 Pa no test required no test required
EN 31092	Water vapour resistance Ret [m <sup>2</sup> Pa/W]	Ret = 38.6 [m <sup>2</sup> Pa/W]	CLASS 1 CLASS 2 CLASS 3	Ret > 40 20 < Ret < 40 Ret < 20