

PITINGA – T-shirt

<p>Description</p>	<ul style="list-style-type: none"> denim effect cotton t-shirt. OEKO-TEX® Standard 100. 		
<p>Maintenance</p>	<p>Maximum wash temperature: 30 °C; Do not bleach; Dry clean with solvents on point F plus Tetrachloroethylene; Tumble drying possible - Drying at lower temperature; Ironing at low temperature (max 110 °C).</p> 	<p>Item</p>	<p>V528-0-00 blue</p>
<p>Standards:</p>			
<p>Sizes</p>		<p>S – 4XL</p>	

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>Description</i>	<i>Cofra result</i>	<i>Minimum requirement / range</i>
<p>Background fabric</p>	<p>EN ISO 1833-1977, SECTION 10</p>	<p>Composition:</p>	<p>Cotton 100%,</p>	
	<p>EN ISO 12127:1996</p>	<p>Fabric mass per unit area</p>	<p>160 ±5% g/m²</p>	
	<p>EN ISO 13688:2013 5.3 ISO 5077:2007/ ISO 6330</p>	<p>Dimensional change (3N-30°C)</p>	<p>-2.1%</p>	<p>±3%</p>
	<p>EN ISO 13688:2013 4.2 (ISO 3071)</p>	<p>The pH's determination from the watery extract</p>	<p>pass</p>	<p>3,5 ≤pH≤ 9,5</p>
	<p>EN ISO 13688:2013 4.2 (EN 14362-1)</p>	<p>Search of the aromatic and carcinogenic amines</p>	<p>Not recording</p>	<p>≤30 ppm</p>
	<p>ISO 105-X11</p>	<p>Colour fastness to hot pressing <i>Colour change</i></p>	<p>Dry: 4 - 5 Wet: 4 - 5</p>	<p>1-5</p>

ISO 105-C06	Colour fastness to Laundering at 40°C			1 - 5
	<i>Colour change</i> 4-5			
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
	wool	4-5		
	EN ISO 105 E04	Colour fastness to perspiration		
<i>Colour change</i>				
<i>Staining:</i>				
diacetate		Acidic	Alkaline	
cotton		4-5	4-5	
nylon		4-5	4-5	
polyester		4-5	4-5	
acrylic		4-5	4-5	
wool		4-5	4-5	