






Tile - short	
Description	<ul style="list-style-type: none"> wide front pockets; 2 back pockets, one of them with flap; pen pocket; hammer loop; side pocket; coin pocket; rule pocket; adjustable waist; YKK[®] zip.
Maintenance	<p>Maximum wash temperature: 60°C; Do not bleach; Dry cleaning allowed; Drying in tumble dryer not allowed; Ironing at low temperature (max 110 °C).</p> <div style="display: flex; justify-content: space-around; align-items: center; margin-top: 10px;">      </div>
item	<p>V068-0-00 khaki/black V068-0-02 navy/black V068-0-03 brown/black V068-0-04 anthracite/black V068-0-05 black/black</p>
Standards	<p>EN ISO 13688:2013</p> <div style="text-align: right; margin-top: 5px;">  </div>
Sizes	<p>44 – 64</p>



SAFETY TECHNICAL SPECIFICATIONS

	Test method	description	Cofra result	minimum requirement / range
Background fabric	EN ISO 1833-1977, SECTION 10	Composition: Cotton/polyester Weave: twill 3/1	60 / 40 % Warp : 8 [yarn/cm] Weft : 6 [yarn/cm]	
	EN ISO 12127:1996	Weight per unit area	245 g/sqm	
	EN ISO 105-C06 E2S: 1994	Colour fastness to washes (60°C)	Colour change: 4 Staining: 4	1 - 5 1 - 5
	EN ISO 105 D01:1993	Colour fastness to dry cleaning	Colour change: 4 – 5	1 - 5
	ISO 5077:1994, ISO 6330: 1994	Dimensional change to washes (60°C)	warp: - 0.8 % weft: - 1.0 %	Max ± 3 % Max ± 3 %
	ISO 105X12: 2001	Colour fastness to rubbing	dry: 5 weft: 4 - 5	1 - 5 1 - 5
	EN ISO 105 B02: 1993, METODO 3	Colour fastness to light	4	1 - 5
	ISO 105-N01:1993	Colour fastness to bleaching	Colour change: 4	1 – 5
	EN ISO 13934-2: 1999	Tensile strength	warp: 1351 N weft: 830 N	400 N 400 N
	EN ISO 13688:2013 4.2 (ISO 3071)	The PH's determination from the watery extract	PH 6.92	3,5<PH≤9,5
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm