

Tolone - PILE JACKET



Description

• pile jacket with membrane • 1 breast pocket • 2 wide front pockets with YKK® zip • elastic waist • reinforced elbows • front opening with YKK® zip

- Breathability coefficients exceed three times the Standard requirements (EN 343 cl.3)

maintenance

maximum wash temperature: 40 °C - do not bleach – do not dry clean – do not dry in a tumble dryer – do not iron.



Item

V130-0-02 navy
V130-0-03 brown
V130-0-04 anthracite
V130- 0-05 black

Standards

EN ISO 13688:2013

Sizes

S – 4XL

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>
Background and colour insert fabric	EN ISO 1833-1977, SECTIONE 10	Composition :	100% polyester + Thermoplastic Polyurethane membrane	
	EN ISO 12127:1996	Weight per unit area	340 g/mq	
	ISO 5077-2007	Dimensional Stability To Washing	Warp: -1,4% Weft: -0,4%	+/- 3%
	ISO 6330-2000	Tensile strength	Warp : 634.8 N Weft: 426.8 N	Warp: 400 N tensile/mass: >=2 Weft: 400 N tensile/mass: >=2
	EN343 clause 4.4 (EN ISO 13934-1)	Tear resistance	Warp: 64 N Weft: 26.6 N	Warp: 25 N Weft: 25 N
	EN343 clause 4.5	Water vapour resistance	19 (class 3)	class 1 : Ret>40 class 2: 20<Ret<40 class 3: Ret<=20
	EN342 clause 4.6 (EN ISO 4674)	Water penetration resistance - Wp [Pa] (before each pretreatment)	>13000 Pa	class1 : Wp >= 8000 Pa class2 : no test required class3 : no test required
	EN343 clause 4.2 (EN 20811)	Water penetration resistance - Wp [Pa] (after each pretreatment)	>13000 Pa (class3)	class1 : no test required class2 : Wp>= 8.000 Pa class3 : Wp >= 13.000 Pa
	ISO 105-X12	Colour fastness to rubbing	Dry: 4-5 Wet: 4	Dry: 4 Wet: 4
	ISO 105-E04	Colour fastness to perspiration	Colour change: 4 - 5 Staining: 4 - 5	Colour change: 4 Staining: 3
	ISO 105-C06	Colour fastness to washes (40 °)	Colour change: 4 - 5 Staining: 4 - 5	Colour change: 3 - 4 Staining: 4 - 5
	EN340/03 paragraph 4.2 (EN 14113)	The PH's determination from the watery extract	PH 7.0	3,5<PH<9,5

TECHNICAL SHEET

EN340/03 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
ISO 105 B02	Colour fastness to Light	4 -5	4 - 5
ISO 105 – N01	Colour Fastness To Bleaching : hypochlorite	Colour change: 4 - 5	Colour change: 4 - 5
EN ISO 12945-1	Pilling Resisance	4 -5	4 -5
ISO 12947-2	Abrasion Resistance Martindale test	> 30000	> 30000